

# 1.2.1 Ezi MULTI FIX





**GOOD PERFORMANCE CEMENTITIOUS ADHESIVE FOR CERAMIC TILES, MOSAIC TILES AND NATURAL STONES**



## DESCRIPTION

Ezi MULTI FIX is a superior range, good performance, coarse grade, water resistant, normal cementitious adhesive (C1). Conforming to the requirements of MS ISO 13007-1, classified as type C1.

## MAIN CHARACTERISTICS

<b>Good</b> Compressive Properties		<b>Good</b> Adhesion Strength	
<b>Water</b> Resistant Properties		<b>Various</b> Application Areas	

## PRODUCT INFORMATION

Name	: Ezi MULTI FIX
Packing	: 25 KG
Classification	: ISO 13007-1 Class C1
Shelf Life	: 12 Months in Dry Condition
Appearance	: Grey Fine Powder
Dry Solid Content	: 100%
pH Value	: Alkaline
Toxicity Hazard	: No
Inflammability	: No

## APPLICATION DATA (Tested at approx. 25 °C)

Mixing Ratio	: 3 pbw. Ezi MULTI FIX to 1 pbw. water (7-8 litres water/EziMIX STAR AD-1 to 25 kg Ezi MULTI FIX)
Consistency of Mix	: Non-Slump Creamy Paste Form
Coverage	: Approx. 8 - 9 m <sup>2</sup> per bag (at 3 mm bed thickness)
Bed Thickness	: Recommended 3 - 6 mm
Slip Resistance	: Excellent
Workability	: Good (Smooth & Non-Slump)
Open Time	: Approx. 15 - 20 minutes
Adjustability Time	: Approx. 15 - 20 minutes
Pot Life	: Approx. 3 - 4 hours
Light Foot Traffic	: Approx. 24 hours
Setting Time	: Approx. 24 - 48 hours
Application Temperature	: From +5 °C to Normal Ambient Temperature

## TECHNICAL DATA (Tested at approx. 25 °C)

Tensile Adhesion Strength after 28 days	Result	Requirement
- Air Dry	: 1.3 ± 0.10 N/mm <sup>2</sup>	≥ 0.5 N/mm <sup>2</sup>
- Water Immersion	: 0.7 ± 0.10 N/mm <sup>2</sup>	≥ 0.5 N/mm <sup>2</sup>
- Heat Aging	: 0.6 ± 0.10 N/mm <sup>2</sup>	≥ 0.5 N/mm <sup>2</sup>
Resistance to Heat	: + 100 °C	
Resistance to Frost	: - 5 °C	
Resistance to Water	: Good	
Resistance to Alkalis	: Good	
Resistance to Acids	: Poor	
Resistance to Oil and Solvent	: Fair	

Tested in accordance to the requirements of MS ISO 13007-1 Type C1

## USAGE

### Suitable to use for :

- variety of ceramic tiles, natural stones and mosaic tiles namely for porous tiles, porcelain tiles, vitrified homogeneous tiles, marbles, granites, glass mosaics, ceramic mosaics, etc.
- bed thickness of 3 - 6 mm, and up to 12 mm in small isolated areas.
- variety of substrates (refer to SUITABLE SUBSTRATES).
- internal and external, wall and floor, dry and wet areas including water immersion areas.

**Note :** - Highly recommended to mix Ezi MULTI FIX with EziMIX STAR AD-1 to achieve optimum performance for installation of low water absorption tiles (≤0.5%) in very demanding situations (e.g. swimming pools, bathrooms, etc.).



## COMPOSITION AND PERFORMANCE

Ezi MULTI FIX consists of grey cement, coarse-graded washed silica sand and selective additives.

Ezi MULTI FIX offers the following benefits when mixed with clean water:

- Good Adhesion Strength
- Good Compressive Properties
- User Friendly
- Good Workability
- Non-Slump Properties
- Prevents Mixing Errors On Site
- Water Resistant Properties
- Reduced Drying Shrinkage
- Minimised Efflorescence

## SUITABLE SUBSTRATES

- (i) **Concrete** - It must be aged for 6 weeks. Direct fixing onto concrete may be adopted provided the surface is flat, cured and free of contamination. Surface primer may be required for direct fixing.
- (ii) **Brick Wall or Lightweight Hollow Blocks** - It must be aged for 4 weeks and levelled with cement-sand mortar prior to fixing tiles. Direct fixing is not recommended.
- (iii) **Aerated Lightweight Concrete Blocks (ALC)** - It must be aged for 4 weeks and levelled with cement-sand mortar (e.g. Ezi ALC PLASTER) prior to fixing tiles. Direct fixing on even surface can be done by using Ezi MULTI FIX + EziMIX STAR AD-1. Prime surface of ALC Blocks with Ezi ALC Primer before direct fixing.
- (iv) **Cement-Sand Render or Screed** - Allow new cement-sand render or screed to cure for 2-3 weeks before tiling. The rendering or screeding mortar mix should ideally be 1 part cement to 3-4 parts of sand.
- (v) **Existing Tiles or Natural Stones** - Existing surface must be dry, sound and free of contamination. Hollow sections should be removed and made well before direct fixing with Ezi MULTI FIX + EziMIX STAR AD-1.
- (vi) **Existing Vinyl Tiles** - Existing surface must be dry, sound and free of contamination. Prime surface with EziMIX SBR BOND, before direct fixing with Ezi MULTI FIX + EziMIX STAR AD-1.
- (vii) **Building Boards** - For example plywood, chipboard, cement-fibre board etc. must be sufficiently braced to provide a rigid substrate. Prime surface with EziMIX SBR BOND, before direct fixing with Ezi MULTI FIX + EziMIX STAR AD-1.
- (viii) **Timber Floor** - It must be rigid, strong and strengthened by overlaying it with a 15 mm thick marine plywood, screw fixed at 300mm centres to the joists. Tiling method is similar to tile installation onto "Building Boards".

*Note:* - Not suitable for use on substrates subjected to high shrinkage, movement, vibration or to install moisture sensitive materials.

- Not recommended to tile over metal, painted surfaces and skim coat plaster.

- Installation in very demanding situations where greater adhesion strength and flexibility are required, recommended to mix Ezi MULTI FIX with latex admixture to replace gauging water.

## INSTALLATION PROCESS



Make sure the surface is clean



Prepare the mix



Spread paste on the substrate



Spread paste on the back of tile

### (1) Preparing the Substrate

- Substrate must be dry, flat and free of contaminants, e.g. dust, grease, laitance, oil, paint, etc.

*Note:* dampen the surface with water only when it has become heated from exposure to sunlight.

- For various substrate preparation, kindly refer to "SUITABLE SUBSTRATES".

### (2) Preparing the Mix

- Mix 3 parts of Ezi MULTI FIX with 1 part of clean water or latex admixture by weight, until a smooth, non-slump paste is achieved. Mechanical mixing is recommended.

### (3) Spreading the Mix


- Spread the paste to the substrate at bed thickness of 3 - 6 mm (may vary depending on tile size and weight) with appropriate notched trowel. It is also applicable up to 12 mm in small isolated areas.

- For tiles or stones of size greater than 300 x 300 mm or subject to heavy loads, spread the adhesive on the back of the tiles or stones to ensure a complete coverage.

- Spread no more than 1 m<sup>2</sup> at a time to prevent Skin-Over. In normal ambient temperature and humidity conditions, the open time of Ezi MULTI FIX is approximately 15 minutes.




Place tile onto the adhesive bed



Good coverage of the adhesive "Solid Bed Fixing"



Adhesive bed is no longer sticky - "Skin-Over"



Applying the grout

*Note:* Unfavourable weather conditions (e.g. extremely hot, strong wind, high temperature, etc.) or highly absorbent substrate can drastically reduce the open time.

### (4) Installing the tiles

- Ceramic tiles should be fixed dry, prior soaking is not required. Recommended to use damp cloth to clean the dusty tile back.

- Tiles should be installed with a firm pressure, and followed by slight twisting action to ensure good coverage and contact of the adhesive (Solid Bed Fixing).

- Tiles must be installed on the fresh adhesive bed within its recommended open time before Skin-Over of the adhesive occurs, resulting in loss of its tackiness. If this happens, discard the affected adhesive bed and apply a fresh adhesive bed.

- Allocate tile joints of approximately 3 mm wide between tiles.

- Remove surplus adhesive from tile surface and joints before it hardens.

- Tiling installed with Ezi MULTI FIX must be protected from water & rain for at least 24 hours.

### (5) Applying the Grout

- Grouting of tile joints with Ezi cementitious or epoxy grouts should commence at least 24 hours after adhesive had set. Setting may be delayed on dense or impervious surfaces.

## MATERIAL SAFETY INFORMATION

A non-toxic, cement-based product which is considered non-hazardous in normal usage. Avoid inhalation, ingestion, skin and eyes contact. For more details, please refer to Ezi Material Safety Data Sheet.

When working with this product, recommended to follow the safety precaution below.



WEAR DUST MASK



WEAR SAFETY GOGGLES



WEAR HAND GLOVES



WEAR SAFETY SHOES



KEEP AWAY FROM CHILDREN

## COMPANY INFORMATION

**MANUFACTURED BY: Ezi MOTARTECH SDN. BHD. (874800-D)**

### FACTORY ADDRESS

**PENANG** : 1888, Jalan Lahar Bubu, Kepala Batas, 13200, Pulau Pinang.  
**IPOH** : PT990, 2 1/2 KM Jln Off Simpang Pulai-Lahat,  
 31300 Kampung Kepayang, Perak Darul Ridzuan.

### SALES OFFICE

**PENANG** : ☎ +604-658 8817 📠 +604-658 8818  
**IPOH** : ☎ +605-357 5818 📠 +605-357 5818  
**KL** : ☎ +602-6277 3709 📠 +603-6272 3760

### Ezi TECHNICAL ADVISORY CENTRE

☎ +6012-431 8221 📠 technical@ezi-fix.com

For more information please log on to: [www.ezi-fix.com](http://www.ezi-fix.com)